

The Manufacturer of Sealing Parts

TEST REPORT

MATERIAL : SIL 70 DURO CLEAR

COMPOUND NO: S7001C

Physical Properties (Press Cure:170°CX10min Post Cure:200°CX4h)	Requirement	Test result
Hardness, Point 硬度(邵A)	65.00~75.00	74.00
Tensile Strength, min, Mpa 拉力強度	6.00	9.10
Ultimate Elongation, min, % 延伸率	150.00	255.00
Specific Gravity, 比重		1.22
Heat Resistance 70h@225°C 老化試驗		
Change in hardness, max, Point 硬度變化(邵A)	+10.00	+1.00
Change in tensile strength, max, % 拉伸強度變化率	-25.00	-20.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-30.00	-15.00
Compression Set 22h@175°C 壓縮永久變形試驗		
Compression set, Method B, max, % 壓縮永久變形	25.00	10.00
Fluid Resistance No.1 Oil Resistance 70h@150°C 1號油試驗		
Change in hardness, Point 硬度變化	-15.00~0.00	-8.00
Change in tensile strength, max, % 拉力強度變化率	-20.00	-5.00
Change in ultimate elongation, max, % 延伸率變化率	-20.00	-5.00
Change in volume, % 體積變化率	0.00~15.00	+6.00
Fluid Resistance No.3 Oil Resistance 70h@150°C 3號油試驗		
Change in hardness, Point 硬度變化	-30.00	-26.00
Change in volume, % 體積變化率	+60.00	+41.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND S7001C CAN MEET ASTM 2000 M5GE706A19B37EO16EO36

