



ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E) Songjiang
Shanghai China
POSTAL CODE: 201613
Tel:(021)57747878
Fax:(021)57747979
Website: http://www.seal.com.tw

TEST REPORT

MATERIAL :FLUOSIL80 DURO BLUE

COMPOUND NO:F8001U

A)PHYSICAL PROPERTIES (PRESS CURE @ 165 DEGREE C X 10 MIN)	REQUIREMENTS	TEST RESULT
HARDNESS SHORE A 硬度	80+/-5	84
TENSILE STRENGTH,Mpa 拉力強度,min	6.0	7.2
ELONGATION,%延伸率,min	150	200
SPECIFIC GRAVITY 比重		1.499
B)HEAT AGING @ 225 DEGREE C X 70 HRS 老化試驗		
HARDNESS CHANGE , 硬度變化	+15	+2
TENSILE STRENGTH CHANGE ,% 拉力強度變化	-45	-10
ELONGATION CHANGE ,% 延伸率變化	-45	-22
C)COMPRESSION SET 壓縮永久變形試驗		
HEAT AGING @ 175 DEGREE C X 22 HRS % ,max	50	9
D)FLUID RESISTANCE,TEST METHOD D471,NO.3 OIL @ 150DEGREE C X 70H 耐 3#油試驗		
HARDNESS CHANGE ,MAX POINTS 硬度變化	0~-10	-1
TENSILE STRENGTH CHANGE ,% 拉力強度變化	-35	-3
ELONGATOIN CHANGE ,% 延伸率變化	-30	+4
VOLUME CHANGE 體積變化	0~+10	+3
E) TT-S-735 TYPE III FUEL RESISTANCE : 23 DEGREE C X22H 燃油試驗		
HARDNESS CHANGE ,MAX POINTS 硬度變化	0~-15	-14
TENSILE STRENGTH CHANGE ,% 拉力強度變化	-60	+0
ELONGATOIN CHANGE ,%延伸率變化	-50	+9
VOLUME CHANGE 體積變化	0~+25	+19

NOTE:THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY.
THIS COMPOUND F8001U CAN MEET ASTM D2000 M2FK806 A19 EF31 EO36

QA Manager: Grace Chen

QC.Dept:Dolly Zhou

