ESCORT SEAL

The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E).,Songjiang
Shanghai China
Postal Code: 201613
Tel:(021)57747878
Fax:(021)51685279
Website: https://www.escort.com.cn/CN

TEST REPORT

MATERIAL : SIL 70 DURO H_TEM RED COMPOUND NO: S7062R

Physical Properties (Press Cure:170℃X10min Post Cure:200℃X4h)	Requirement	Test result
Hardness,Point 硬度(邵A)	65.00~75.00	72.00
Tensile Strength,min,Mpa 拉力強度	6.00	9.70
Ultimate Elongation,min,% 延伸率	150.00	279.00
Specific Gravity, 比重		1.19
Heat Resistance 70h@225℃ 老化試驗		
Change in hardness,max,Point 硬度變化(邵A)	+10.00	+2.00
Change in tensile strength,max,% 拉伸強度變化率	-25.00	-9.00
Change in ultimate elongation,max,% 扯斷伸長率變化率	-30.00	-16.00
Compression Set 22h@175℃ 壓縮永久變形試驗		
Compression set,Method B,max,% 壓縮永久變形	25.00	9.00
Fluid Resistance No.1 Oil Resistance 70h@150℃ 1號油試驗		
Change in hardness,Point 硬度變化	-15.00~0.00	-7.00
Change in tensile strength,max,% 拉力強度變化率	-20.00	-6.00
Change in ultimate elongation,max,% 延伸率變化率	-20.00	-2.00
Change in volume,% 體積變化率	0.00~15.00	+7.00
Fluid Resistance No.3 Oil Resistance 70h@150℃ 3號油試驗		
Change in hardness,Point 硬度變化	-30.00	-19.00
Change in volume,% 體積變化率	+60.00	+42.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY

THIS COMPOUND S7062R CAN MEET ASTM 2000 M5GE706A19B37EO16EO56

QA Manager: Grace Chen **QC.Dept:** LingLing.Li **Test by:** QC08