

The Manufacturer of Sealing Parts

TEST REPORT

MATERIAL : HNBR 90 DURO L_Tem(-45) BLACK

COMPOUND NO: H9063B

Physical Properties (Press Cure:170°CX10min Post Cure:150°CX4h)	Requirement	Test result
Hardness, Point 硬度(邵A)	85.00-95.00	93.00
Tensile Strength, min, Mpa 拉力強度	10.00	17.40
Ultimate Elongation, min, % 延伸率	100.00	117.00
Specific Gravity, 比重		1.32

Heat Resistance 70h@150°C 老化試驗

Change in hardness, max, Point 硬度變化(邵A)	+10.00	+0.00
Change in tensile strength, max, % 拉伸強度變化率	-15.00	+3.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-25.00	-13.00

Fluid Resistance No.1 Oil Resistance 70h@150°C 1號油試驗

Change in hardness, Point 硬度變化	-5.00-10.00	-1.00
Change in tensile strength, max, % 拉力強度變化率	-20.00	-1.00
Change in ultimate elongation, max, % 延伸率變化率	-30.00	-6.00
Change in volume, % 體積變化率	-10.00-5.00	+0.00

Fluid Resistance No.3 Oil Resistance 70h@150°C 3號油試驗

Change in hardness, Point 硬度變化	-15.00	-15.00
Change in tensile strength, max, % 拉力強度變化率	-40.00	-10.00
Change in ultimate elongation, max, % 延伸率變化率	-30.00	+2.00
Change in volume, % 體積變化率	+25.00	+25.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
 THIS COMPOUND H9063B CAN MEET ASMT 2000 M4DH910A26B16EQ16EO36

