

The Manufacturer of Sealing Parts

TEST REPORT

MATERIAL : FKM 60 DURO BLACK

COMPOUND NO: V6001B

Physical Properties (Press Cure:170°CX10min Post Cure:230°CX24h)	Requirement	Test result
Hardness, Point 硬度(邵A)	55.00-65.00	62.00
Tensile Strength, min, Mpa 拉力強度	7.00	8.00
Ultimate Elongation, min, % 延伸率	200.00	222.00
Specific Gravity, 比重		1.81
Heat Resistance 70h@250°C 老化試驗		
Change in hardness, max, Point 硬度變化(邵A)	+10.00	+0.00
Change in tensile strength, max, % 拉伸強度變化率	-25.00	+0.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-25.00	-2.00
Compression Set 22h@175°C 壓縮永久變形試驗		
Compression set, Method B, max, % 壓縮永久變形	50.00	4.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
THIS COMPOUND V6001B CAN MEET ASTM 2000 M2HK607A1-10B37

