

The Manufacturer of Sealing Parts

TEST REPORT

MATERIAL : HNBR 70 DURO GREEN

COMPOUND NO: H7001G

Physical Properties (Press Cure:170°CX10min Post Cure:175°CX4h)	Requirement	Test result
Hardness, Point 硬度(邵A)	65.00~75.00	75.00
Tensile Strength, min, Mpa 拉力強度	10.00	19.10
Ultimate Elongation, min, % 延伸率	200.00	242.00
Specific Gravity, 比重		1.26
Heat Resistance 70h@150°C 老化試驗		
Change in hardness, max, Point 硬度變化(邵A)	+10.00	+3.00
Change in tensile strength, max, % 拉伸強度變化率	-25.00	+9.00
Change in ultimate elongation, max, % 扯斷伸長率變化率	-30.00	-1.00
Compression Set 22h@150°C 壓縮永久變形試驗		
Compression set, Method B, max, % 壓縮永久變形	30.00	11.00
Fluid Resistance No.1 Oil Resistance 70h@150°C 1號油試驗		
Change in hardness, Point 硬度變化	-5.00~10.00	+1.00
Change in tensile strength, max, % 拉力強度變化率	-20.00	-9.00
Change in ultimate elongation, max, % 延伸率變化率	-30.00	-15.00
Change in volume, % 體積變化率	±5.00	-5.00
Fluid Resistance No.3 Oil Resistance 70h@150°C 3號油試驗		
Change in hardness, Point 硬度變化	-15.00	-7.00
Change in tensile strength, max, % 拉力強度變化率	-30.00	-24.00
Change in ultimate elongation, max, % 延伸率變化率	-30.00	-17.00
Change in volume, % 體積變化率	+25.00	+12.00

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY
 THIS COMPOUND H7001G CAN MEET ASMT 2000 M3DH710A26B16EO16EO36

